

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/IL05/000554

International filing date: 30 May 2005 (30.05.2005)

Document type: Certified copy of priority document

Document details: Country/Office: IL
Number: 162450
Filing date: 10 June 2004 (10.06.2004)

Date of receipt at the International Bureau: 07 July 2005 (07.07.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

87.6



PCT/IL 2005 / 000554

מדינת ישראל
STATE OF ISRAEL

Ministry of Justice
Patent Office

משרד המשפטים
לשכת הפטנטים

This is to certify that
annexed hereto is a true
copy of the documents as
originally deposited with
the patent application
particulars of which are
specified on the first page
of the annex.

זאת לתעודה כי
רצופים בזה העתקים
נכונים של המסמכים
שהופקדו לכתחילה
עם הבקשה לפטנט
לפי הפרטים הרשומים
בעמוד הראשון של
הנספח.

This 08-05-2005 היום


רשם הפטנטים

Commissioner of Patents

ד"ר מאיר כהנא

רשם הפטנטים, המזגמים וטיפוגרפי המסמכים

נתאשר
Certified



לשימוש הלישכה
For Office Use

מספר: 162450
Number

תאריך: 10-06-2004
Date

הוקדם/נדחה
Ante/Post-Dated

Inventors: ממציאים:

1. ברון שמואל

BRON Samuel

2. סלושני אריאל

SLUSZNY Ariel

3. פלד דורית

PELED Dorit

4. פרלה דורית

PERLE Dorit

חוק הפטנטים, תשכ"ז-1967

Patent Law, 5727 - 1967

בקשה לפטנט

Application for Patent

אני, (שם המבקש, מענו ולגבי גוף מאוגד - מקום התאגדות)

I, (Name and address of applicant, and in case of body corporate-place of incorporation)

BROMINE COMPOUNDS LTD

תרכובות ברום בע"מ

MAKLEFF HOUSE.

בית מקלף

P.O. Box 180

ת.ד. 180

Beer-Sheva

באר-שבע

Owner, by virtue of
of an invention the title of which is

THE LAW

ה די

בעל ההמצאה מכח
ששמה הוא

מניעת דהיה בקצפים פוליאורתניים גמישים

(בעברית)
(Hebrew)

(באנגלית)
(English)

SCORCH PREVENTION IN FLEXIBLE POLYURETHANE FOAMS

מבקש בואת כי ינתן לי עליה פטנט hereby apply for a patent to be granted to me in respect thereof.

*בקשת חלוקה - Application of Division		*דרישה דין קדימה Priority Claim		
*בקשת פטנט מוסף - Application for Patent Addition				
*מבקשת פטנט from Application		מספר/סימן Number/Mark	תאריך Date	מדינת האגוד Convention Country
מס' _____ dated _____				
*יפוי כח: כללי / מיוחד - רצוף / בזה / נוד יוגש P.O.A.: general / individual - attached / to be filed later הוגש בעניין _____ 159196 _____				
המען למסירת מסמכים בישראל Address for Service in Israel לוצאטו את לוצאטו ת.ד. 5352 באר שבע 84152 מספרנו: 17660/04				
חתימת המבקש Signature of Applicant		היום 9 בחודש יוני שנה 2004 of the year of This		
Luzzatto & Luzzatto By: _____ Attorneys for Applicant		לשימוש הלישכה		

טופס זה כשהוא מוטבע בחותם לישיבת הפטנטים ומושלם במספר ובתאריך ההגשה, הינו אישור להגשת הבקשה שפרטיה רשומים לעיל.
This form, impressed with the Seal of the Patent Office and indicating the number and date of filing, certifies the filing of the application the particulars of which are set out above.

#342127

* מחק את המיותר Delete whatever is inapplicable

7660/04

מניעת דהיה בקצפים פוליאורתנניים גמישים

SCORCH PREVENTION IN FLEXIBLE POLYURETHANE FOAMS

SCORCH PREVENTION IN FLEXIBLE POLYURETHANE FOAMS

Field of the Invention

The present invention relates to the prevention of discoloration in flexible polyurethane foams, a phenomenon commonly referred to as "scorching". More particularly, the invention relates to novel compositions useful to alleviate or prevent the aforementioned undesirable effect.

Background of the invention

Scorching is an undesirable discoloration phenomenon which occurs within the foam blocks, causing them to assume a yellow to brown color. This discoloration is especially apparent in the center of the blocks where the internal temperatures remain high for a relatively long period of time. The exposure of the interior of the foams to high temperatures leads to embrittlement and the core discoloration commonly known as scorching. In extreme cases this can result in ignition of the foam buns, sometimes with disastrous consequences. In some severe cases, it can cause a degradation of physical properties or, where scorching is particularly intense, can result in spontaneous combustion of freshly made foam blocks. Flame retardants, with few exceptions, e.g., pentabromodiphenyl oxide, exacerbate the "scorch" problems that arise during processing of low density foams.

It is known that the use of flame retardants (FR) in polyols can lead to even higher discoloration in polyurethane (PU) foams than the non FR grades. Flame retardants, with few exceptions, create two major problems for the manufacturers of water-blown, flexible, slab stock foam. They increase the "scorch" problems that arise during processing of low density foams and they increase the smoldering tendency of foams subjected to the California TB 117 standard.

The flame-retardant tribromoneopentyl alcohol (known as FR-513 ex Dead Sea Bromine Group (DSBG)) was investigated as flame retardant in PU foams already in 1975 [J. H. Botkin, Scorch Inhibitors for Polyurethane Slabstock Foams, Adv. Urethane Sci. Technol., vol. 14, pp. 57-80, 1998].

The use of antioxidants has been proposed in the art and it can mitigate to some extent the increased scorch and discoloration in flame retarded polyols and foams. However, the literature and experiments carried out by the inventors indicate that antioxidants by themselves are not very efficient when halogen containing flame retardants, are present in the formulation. Thus, the art has so far failed to provide an efficient solution to the problem of scorch taking place during the manufacturing of flexible polyurethane foams.

It is an object of the present invention to provide an anti-scorch composition that efficiently addresses the problem of scorch for flexible polyurethane formulations flame retarded with halogen-containing flame retardants.

It is another object of the invention to provide an anti-scorch combination that overcomes the drawbacks of the prior art.

It is yet another object of the invention to provide a method for preventing or diminishing the occurrence of scorch during the manufacturing of flexible polyurethane foams.

Other purposes and advantages of the invention will become apparent as the description proceeds.

Summary of the invention

The invention is directed to an anti-scorch composition for flame-retarded flexible polyurethane foams, comprising, in combination, one or more antioxidant agents, together with one or more salt(s) of an organic acid.

According to a preferred embodiment of the invention the organic acid is selected from among saturated or unsaturated, aliphatic or aromatic mono-

or di-carboxylated acids. According to another preferred embodiment of the invention the salt of the organic acid is a salt of Ca, Zn, Ba or Sn.

Illustrative and non-limitative examples of antioxidant agents are phenols and amino oxygen scavengers, such as hindered phenols.

Illustrative and non-limitative examples of amino oxygen scavengers include alkylated diphenylamines.

According to a preferred embodiment of the invention the flame-retardant is a halogen-containing flame retardant, such as – but not limited to – tribromoneopentyl alcohol.

According to a further preferred embodiment of the invention the composition further comprises an epoxy compound, such as – but not limited to – diglycidyl ether of bisphenol A and its derivatives.

In another aspect the invention is directed to a method for preventing or diminishing scorch in a flame-retarded flexible polyurethane foam, comprising adding to the polyurethane composition, prior to foaming, one or more antioxidant agents, together with one or more salt(s) of an organic acid, as hereinbefore defined.

The above and other objects and advantages of the invention will be better understood from the following illustrative and non-limitative examples.

Test Procedure:

MW test protocol for scorch evaluation

The test method consists of the following steps:

1. Foam production in a small shoe box with a square cross-section
2. Immediately after the foam rise is complete (usually less than 2 minutes), the foam is heated using a microwave (MW) oven using a predetermined time and power level.
3. The foam is then heated in an oven at $120 \pm 2^\circ\text{C}$ for 2 min.
4. The foam is allowed to cure at RT (room temperature) for an additional 15 min.
5. By the end of the RT curing time the foam is cut (usually vertically) and the scorch is observed.

Scorch evaluation

The scorch is evaluated using two methods:

1. The foam is photographed using a digital camera. This allows for a visual comparison between the scorch of a reference formulation and the scorch of the formulation under investigation.
2. The foam color is analyzed using a spectrophotometer. The results are expressed in the usual color space: L^*a^*b and performed accordingly to ASTM D-2244.

Note: the scorch intensity may change from day to day according to the physical conditions of the surroundings in which the foam has been prepared (usually the temperature and relative humidity). This is why it is customary to prepare each day a reference sample.

Example

Foam preparation

The mixture was prepared in a 0.65 l disposable cup. The components were added one at a time starting with the polyol. The mixture was vigorously mixed at 3500 rpm for 10 seconds following the addition of each component, not including the Toluene diisocyanate (TDI). After the addition of TDI, the mixture was mixed for an additional 10 sec and then poured into a 25X25X17 cm cardboard box. The times between the TDI addition and the pouring into the cardboard box and the end of the foam blowing (rise time) were monitored.

Comparative Samples and Results

The effect of the antiscorching ingredients and their combinations was measured on the darkest areas on the foam after microwave oven treatment, using a spectrophotometer which provides color measurements expressed in the L*a*b color space. The most relevant color parameters for scorch assessment are Δb and ΔE .

The color parameters are given as normalized values relative to the reference specimens. As explained in the MW oven procedure, this particular method for scorch propensity assessment requires that a new reference foam be prepared, subjected to MW oven procedure and measured in each and every day of measurements. This requirement is related to the effect various experimental conditions, such as the temperature and the relative humidity of the air in the lab may have on the level of scorch. The normalized Δb and ΔE differences between a reference foam (containing no antiscorching ingredients) and foams containing various ingredients with antiscorch effects, are calculated as follows:

$$\Delta\Delta b(\text{normalized}) = \frac{\Delta b(\text{reference}) - \Delta b(\text{sample})}{\Delta b(\text{reference})} \cdot 100$$

$$\Delta\Delta E(\text{normalized}) = \frac{\Delta E(\text{reference}) - \Delta E(\text{sample})}{\Delta E(\text{reference})} \cdot 100$$

Note: a value greater than 100 can sometimes emerge from these calculations since both Δb and ΔE for each specimen are compared to a factory white standard. The higher the $\Delta\Delta b$ and $\Delta\Delta E$ values, the lower the scorch.

Formulations for two grades of foams are shown in Tables I and II: Medium density foams (Table I) have a density of approximately 25 Kg/m³; Low density foams (Table II) have a density of approximately 15 Kg/m³.

Ingredients: AO1 and AO5 are antioxidants produced by Goldschmidt (Degussa) and contain combinations of hindered phenols and aromatic diamines.

Epoxy 828 is Diglycidyl ether of bisphenol A (DGEBA).

ESBO = Epoxidized Soya Bean oil.

All other ingredients below the FR-513 line in the table are metallic salts (Ca, Zn, Ba, Ti) of organic acids.

Table I
Normal density foams

Ingredient	1	2	3	4	5	6	7	8	9
Polyol	100	100	100	100	100	100	100	100	100
Water	4.2	4.2	4.2	4.2	4.2	4.2	4.2	4.2	4.2
Silicon 8228	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
Amine Dabco 33LV	0.09	0.09	0.09	0.09	0.09	0.09	0.09	0.09	0.09
Amine BDE	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03
Tin T-9	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25
Toluene di-isocyanate (TDI)	56.31	56.31	56.31	56.31	56.31	56.31	56.31	56.31	56.31
FR-513	5	5	5	5	5	5	5	5	5
AO5	0.42	0.21	0.85						
Calcium stearate (CaSt)	0.42	0.21							
PK4610	0.42	0.21							
Epoxy 828			0.85		0.1	0.1	0.21		
ESBO				1.7					
LZB 138					0.21			0.21	0.21
AO 1					0.21	0.21	0.21	0.21	0.21
CZ400						0.21		0.21	
CZ 118 S							0.21		0.21
ΔΔb	90.13	106.1	49.17	-132.6	82.32	77.06	93.93	84.58	102.9
ΔΔE	17.04	10.84	18.34	-99.43	27.61	32.67	30.14	37.42	33.98

Table II
Low density foams

	1	2	3	4	5	6
Polyol	100	100	100	100	100	100
Water	5.25	5.25	5.25	5.25	5.25	5.25
Silicon 8228	1.0	1.0	1.0	1.0	1.0	1.0
Amine Dabco 33LV	0.06	0.06	0.06	0.06	0.06	0.06
Amine BDE	0.046	0.046	0.046	0.046	0.046	0.046
Tin T-9	0.37	0.37	0.37	0.37	0.37	0.37
Methylene Chloride (MeCl)	11	11	11	11	11	11
TDI	71.1	71.1	71.1	71.1	71.1	71.1
FR-513	15	15	15	15	15	15
AO5			0.1	0.3		0.2
Epoxy 828	0.5	1.0				
BM270					1.0	0.2
LZB287						0.6
$\Delta\Delta b$	-14.11	24.37	-15.10	-77.1	95.29	50.90
$\Delta\Delta E$	0	13.73	-10.13	-41.03	27.80	11.70

From the results in Tables I and II it is clearly seen that the compositions of the invention attain a substantial improvement.

The notations and composition of materials used as antiscorch ingredients in the examples in Tables I and II are detailed in Table III.

Table III - Composition of ingredients used as antiscorch materials

Producer	Name	Ingredients		State
Akcros	Lankromark LZB287	1) Barium oleate Barium t-butylbenzoate	40%	Liquid
		2) Zinc 2-ethylhexanoate	5-10%	
		3) Phosphite esters	20-40%	
		4) 2-(2-butoxyethoxy) ethanol	5-10%	
		5) Phenol	5-10%	
	Lankromark LZB413	1) Barium 2-ethylhexanoate Barium oleate Barium t-butylbenzoate	20%	Liquid
		2) Zinc 2-ethylhexanoate	1-5%	
		3) Zinc t-butylbenzoate	1-5%	
		4) Phosphite esters	20-40%	
		5) Trisnonylphenyl phosphite	1-5%	
		6) 2-(2-butoxyethoxy ethanol)		
	Lankromark LZB138	1) Barium compounds (% as barium metal)	2-15%	Liquid
		2) Phenol	1-5%	
	Lankroflex E2307	1) Epoxidised soya bean oil	> 99%	Liquid
	Tinstab BTS71S	1) n-Butyltin tris (2-ethylhexylthio- glycolate)	~20 %	Liquid
		2) Di-n-butyltin bis (2-ethylhexylthio- glycolate)	~70%	
	Tinstab BM270	1) Di-n-butyltin bis (methylmaleate)	~95%	Liquid
Shell	Epoxy 828		~100%	Liquid
Goldschmidt	Ortegol AO1	Steric hindered phenol derivate	66.7%	
		Alkylated diphenylamine	33.3%	
	Ortegol AO5	Steric hindered phenol derivate	70-72%	
		Alkylated diphenylamine	20-22%	
Crompton	Mark CZ 400 (Ca/Zn stabilizer)	2-(2-Butoxyethoxy)ethanol	<10%	Liquid
		Alkylarylphosphites	55-65%	
		Calcium 4-(1,1-dimethylethyl)benzoate	<10%	
	Mark CZ 118S (Ca/Zn stabilizer)	Tris(nonylphenyl)phosphite	30-40%	Liquid
		Other components - not listed		
	Mark BZ 592 (Ba/Zn stabilizer)	Solvent naphta, light aromatic	<10%	Liquid
		Barium compounds	35-45%	
		Triisodecyl phosphite	<25%	

Table III - Composition of ingredients used as antiscorch materials (cnt'd)

Producer	Name	Ingredients		State
Crompton	Mark BZ 562 (Ba/Zn stabilizer)	Solvent naphta, light aromatic	<10%	Liquid
		Alkylarylphosphites	20-30%	
		Zinc bis(p-nonylphenolate)	<3%	
		Barium compounds	35-45%	
	Mark BZ 555 (Ba/Zn stabilizer)	Tris(2-ethylhexylmercaptoacetate) phosphate	5-15%	Liquid
		Diisodecyl phenyl phosphite	25-35%	
		Solvent naphta, light aromatic	5-15%	
		Barium compounds	20-30%	
	Mark BZ 563 (Ba/Zn stabilizer)	Diisodecyl phenyl phosphite	30-50%	Liquid
		2-(2-Butoxyethoxy)ethanol	<5%	
		Zinc bis(p-nonylphenolate)	<5%	
		Barium compounds	20-30%	

Example 3 in Table I and Examples 3 and 4 in Table II, respectively, demonstrate that the use of a conventional antioxidant, i.e. a mixture of hindered phenols and alkylated diphenyldiamines, alone or together with an epoxy moiety, does not prevent scorch in a bromine-containing FR formulation. Epoxy alone, either as DGEBA or ESBO, are not effective either (Examples 4 in Table 1, and Examples 1 and 2 in Table II). However, addition of metallic salts of various organic acids, significantly improves the resistance to scorch of a polyurethane flexible foam formulation including a bromine-containing flame retardant (Examples 8, 9 - Table I, and Examples 5, 6 - Table II).

All the above description has been provided for the purpose of illustration, and is not intended to limit the invention in any way. Various modifications can be carried out in the method and system according to the invention, without departing from its spirit.

CLAIMS

1. An anti-scorch composition for flame-retarded flexible polyurethane foams, comprising, in combination, one or more antioxidant agents, together with one or more salt(s) of an organic acid.
2. A composition according to claim 1, wherein the organic acid is selected from among saturated or unsaturated, aliphatic or aromatic mono- or dicarboxylated acids.
3. A composition according to claim 2, wherein the salt of the organic acid is a salt of Ca, Zn, Ba or Sn.
4. A composition according to any one of claims 1 to 3, wherein the antioxidant agent(s) is selected from among phenols and amino oxygen scavengers.
5. A composition according to claim 4, wherein the phenol is a hindered phenol.
6. A composition according to claim 4, wherein the amino oxygen scavenger is an alkylated diphenylamine.

7. A composition according to claim 1, wherein the flame-retardant is a halogen-containing flame retardant.
8. The composition of claim 7, wherein the flame-retardant is tribromoneopentyl alcohol.
9. A composition according to any one of claims 1 to 8, further comprising an epoxy compound.
10. A composition according to claim 9, wherein the epoxy compound is selected from among diglycidyl ether of bisphenol A and its derivatives.
11. A method for preventing or diminishing scorch in a flame-retarded flexible polyurethane foam, comprising adding to the polyurethane composition, prior to foaming, one or more antioxidant agents, together with one or more salt(s) of an organic acid.
12. A method according to claim 11, wherein the organic acid is selected from among saturated or unsaturated, aliphatic or aromatic mono- or dicarboxylated acids.
13. A method according to claim 12, wherein the salt of the organic acid is a salt of Ca, Zn, Ba or Sn.

14. A method according to any one of claims 11 to 13, wherein the antioxidant agent(s) is selected from among phenols and amino oxygen scavengers.

15. A method according to claim 14, wherein the phenol is a hindered phenol.

16. A method according to claim 14, wherein the amino oxygen scavenger is an alkylated diphenylamine.

17. A method according to claim 11, wherein the flame-retardant is a halogen-containing flame retardant.

18. The method of claim 17, wherein the flame-retardant is tribromoneopentyl alcohol.

19. A method according to any one of claims 11 to 18, further comprising adding an epoxy compound.

20. A method according to claim 19, wherein the epoxy compound is selected from among diglycidyl ether of bisphenol A and its derivatives.

21. A method for preventing or diminishing scorch in a flame-retarded flexible polyurethane foam, substantially as described and illustrated.

22. An anti-scorch composition for flame-retarded flexible polyurethane foams, essentially as described and illustrated and with particular reference to the examples.

לוצאטו און לוצאטו
LUZZATTO & LUZZATTO

By



ע"י